arXiv:cond-mat/0009138v2 [cond-mat.mtrl-sci] 15 Sep 2000

Hydrodynamics of crystals with interstitials

G.L Buchbinder[*]
Department of Physics, Omsk State University, Peace Avenue 55-a 644077, Omsk, Russia

(February 1, 2008)

The hydrodynamic equations for a crystals with interstitials, taking into account the dissipative processes of the viscosity, heat conduction and the interstitial diffusion are derived. To achieve that we use the phenomenological approach has originally been applied in the theory of the superfluids for the derivation of equations of the two-fluid hydrodynamics. On the basis of obtained equations the problem of the propagation of plane waves in the crystal with low interstitial concentration has been considered. For the case when effects of the viscosity and the heat conduction are absent and the diffusion mobility of interstitials is small the absorption coefficient of longitudinal sound wave has been calculated.

PACS numbers: 46.05.+b, 62.30.+d

A great number of various in its nature processes occuring in the bulk and on the surface of the crystalline solids can be considered within the scope of the hydrodynamic description[1–11]. The presence of the slowly varying spatial and temporal disturbances in the system allows us to describe the nonequilibrium behavior in terms of a few slow, hydrodynamic variables. One of the most important hydrodynamic processes is the diffusion of interstitials in the crystalline lattice. Within the scope of the hydrodynamic approximation their dynamics is commonly determined by the well known diffusion equation rested on the classical Fick's laws. This equation is closed with respect to the interstitial concentration and the presence of the lattice is only manifested at the calculation of the diffusion coefficient for the specific microscopic model. Such an approach, justified in the case of the low impurity concentrations and weak inhomogeneity in the system proves to be unfit at the finite concentration and the large gradients. In the case the interaction between the impurity system and the lattice is also manifested at the macroscopic level through the deformation of the crystal. Therefore at the finite interstitial concentration the dynamics of interstitials is to be considered in common with motion of the lattice. As a result the hydrodynamic equations describing the corresponding process are to contain both the interstitial and lattice variables.

In this paper we shall obtain hydrodynamic equations for the crystal containing interstitials. With that end in view we use the method has originally been applied in the theory of the superfluids[12,13] for the derivation of the equations of the two-fluid hydrodynamics and then employed for supersolids[14]. It gives a possibility to obtain equations describing the dynamics of interstitials relative to the moving lattice.

On the basis of the found equations we shall consider the propagation of plane waves in the crystal and in the simplest approximation calculate the sound velocities and absorption coefficient caused by a diffusion of interstitials.

We assume that the concentration of vacancies is negligible and the nonequilibrium state of the crystal is characterized by the mass densities of impurity particles ρ_p and lattice atoms ρ_L and denote by $\mathbf{j}$ the current density of the medium (lattice plus interstitials).

$$\mathbf{j} = \rho_L \mathbf{v}_L + \rho_p \mathbf{v}_p \,, \tag{1}$$

where $\mathbf{v}_L$ and $\mathbf{v}_p$ are the velocity fields of the lattice and the impurity system, respectively.

The complete set of the hydrodynamic equations has to contain the local conservation laws of mass, momentum and equation for the entropy, following from the second law of the thermodynamics. We write down the corresponding balance equations as

$$\frac{\partial \rho}{\partial t} + \operatorname{div} \mathbf{j} = 0 \,, \tag{2}$$

$$\frac{\partial j_i}{\partial t} + \frac{\partial \Pi_{ik}}{\partial x_k} = 0 \,, \tag{3}$$

$$\frac{\partial S}{\partial t} + \operatorname{div} \left(S\mathbf{v} + \frac{\mathbf{q}}{T} - \frac{\nu}{\rho T}\mathbf{J}\right) = \frac{R}{T} \,, \tag{4}$$

here $\rho = \rho_L + \rho_p$ is the total mass density of the medium, $\mathbf{v} = \rho^{-1}\mathbf{j}$ is the mass velocity, S is the entropy density of the medium, Π_{ik} is the tensor momentum current density, $\mathbf{q}$ is the heat current density, $\mathbf{J}$ is the diffusion current density of interstitials defined as

$$\mathbf{J} = \rho_p(\mathbf{v}_p - \mathbf{v}) \,,$$

ν is the chemical potential of interstitials per unite volume, T is absolute temperature and R $(R > 0)$ is the dissipative function of the medium; summation over the repeated indexes is implied.

In addition, the system of equations (2) - (4) has to be supplemented by the continuity equation for the interstitial density and equation of motion for the lattice

$$\frac{\partial (c\rho)}{\partial t} + \operatorname{div} c\rho \mathbf{v}_p = 0 \,, \tag{5}$$

$$\frac{\partial (\rho_L v_{Li})}{\partial t} + \frac{\partial \Pi_{Lik}}{\partial x_k} = f_i \,, \tag{6}$$

where $c = \rho_p/\rho$ is the interstitial concentration, $\mathbf{f}$ is the mass force with which the impurity system acts on the lattice; Π_{Lik} is the tensor momentum current density of the lattice which we take in the form

$$\Pi_{Lik} = \rho_L v_{Li} v_{Lk} - \sigma_{ik} - \sigma'_{ik}\,, \tag{7}$$

where σ_{ik} is the symmetric, elastic stress tensor of the lattice

$$\begin{aligned} \sigma_{ik} &= -p_L \delta_{ik} + \tilde{\sigma}_{ik}\,, \\ p_L &= -\frac{1}{3}\sigma_{ii}, \qquad \mathrm{Tr}\,\tilde{\sigma} = \tilde{\sigma}_{ii} = 0\,, \end{aligned} \tag{8}$$

and σ'_k describes the effect of the viscosity. Both σ_{ik} and σ'_{ik} are supposed to be known. Here and further the tilde is used to denote the traceless part of a tensor.

Now let us introduce the vector $\mathbf{u}$ defining displacement of lattice sites and connected with velocity field $\mathbf{v}_L$ by relationship

$$\mathbf{v}_L = \frac{d\mathbf{u}}{dt} = \frac{\partial \mathbf{u}}{\partial t} + (\mathbf{v}_L \cdot \nabla)\mathbf{u}\,. \tag{9}$$

The variables ρ, S, T, c, $\mathbf{j}$, $\mathbf{u}$ completely define the nonequilibrium state of the system and satisfy equations (2) - (6). Similarly to Ref.[12] we shall find the remaining unknown values Π_{ik}, R, $\mathbf{q}$, $\mathbf{J}$, $\mathbf{f}$ so that the conservation energy law

$$\frac{\partial E}{\partial t} + \mathrm{div}\,\mathbf{Q} = 0\,, \tag{10}$$

with E and $\mathbf{Q}$ being energy density and energy current density, respectively, would follow from Eqs.(2) - (6). In the Eq.(10) the current $\mathbf{Q}$ is originally unknown as well.

To determine the form of the unknown values indicated above we shall pass to the new frame moving with velocity $\mathbf{v}_L$, in which the velocity of the lattice of the given element of the medium is equal zero. The energy E and the momentum density $\mathbf{j}$ are related by the Gallilean transformation to its values E_0 and $\mathbf{j}_0$ in the frame where the lattice rests by relationships

$$E = \frac{\rho v_L^2}{2} + \mathbf{j}_0 \mathbf{v}_L + E_0\,, \tag{11}$$

$$\mathbf{j} = \rho \mathbf{v}_L + \mathbf{j}_0\,; \qquad \mathbf{j}_0 = \rho_p(\mathbf{v}_p - \mathbf{v}_L)\,. \tag{12}$$

Let us write down the differential of E_0, considered as a function of S, ρ, c, $\mathbf{j}_0$ and the infinitesimal strain tensor u_{ij}, in the form

$$dE_0 = T dS + \mu d\rho + \nu dc + \tilde{\sigma}_{ij} d\tilde{u}_{ij} + \mathbf{w} d\mathbf{j}_0\,, \tag{13}$$

here μ is the chemical potential of the medium and $\mathbf{w} = \mathbf{v}_p - \mathbf{v}_L$ is the relative velocity. In the Eq. (13) it has been taken into account that the variation du_{ii} of sum of diagonal components of the strain tensor u_{ij} is determined by the variation of the density $d\rho$.

Differentiating the Eq.(11) with respect to time and using Eqs. (2) - (13), one obtains

$$\begin{aligned} \frac{\partial E}{\partial t} = {} & (\mathbf{v}_p \mathbf{v}_L - \frac{v_L^2}{2} - \mu + \frac{c\nu}{\rho})\,\mathrm{div}\,\mathbf{j} - \mathbf{w}\mathbf{f} \\ & + \rho_L w_i (\mathbf{v}_L \cdot \nabla) v_{Li} - w_i \frac{\partial}{\partial x_k}(\sigma_{ik} + \sigma'_{ik}) \\ & - v_{pi}\frac{\partial \Pi_{ik}}{\partial x_k} + \tilde{\sigma}_{ij}\frac{\partial u_{ij}}{\partial t} + \frac{\nu}{\rho}\mathrm{div}\, c\rho \mathbf{v}_p \\ & - T\mathrm{div}(S\mathbf{v} + \frac{\mathbf{q}}{T} - \frac{\nu}{\rho T}\mathbf{J}) + R \end{aligned}$$

The last equality after long and tedious, though simple, transformations is led to the form

$$\begin{aligned} \frac{\partial E}{\partial t} & + \mathrm{div}\Big\{ (\frac{v_L^2}{2} + \mu + \frac{TS}{\rho})\,\mathbf{j} + \rho_p \mathbf{v}_p (\mathbf{v}_p \cdot \mathbf{w}) \\ & + \mathbf{q} - \mathbf{v}_L \cdot (\tilde{\sigma} + \sigma') + \mathbf{v}_p \cdot \pi \Big\} \\ & = \Big[R - \sigma'_{ik}\frac{\partial v_{Li}}{\partial x_k} + \pi_{ik}\frac{\partial v_{pi}}{\partial x_k} + \frac{\mathbf{q}\nabla T}{T} \\ & \qquad + T\mathbf{J}\nabla\Big(\frac{\nu}{\rho T}\Big)\Big] \\ & - \mathbf{w}\Big[\mathbf{f} - \nabla p_L + \rho_L(\nabla \mu + \frac{S\nabla T}{\rho}) \\ & \qquad - \rho_L \frac{\nu}{\rho}\nabla c + \tilde{u}_{ij}\nabla \tilde{\sigma}_{ij} \Big]\,, \end{aligned} \tag{14}$$

where π_{ik} is defined from the equality

$$\begin{aligned} \Pi_{ik} = {} & \rho_L v_{Li} v_{Lk} + \rho_p v_{pi} v_{pk} + p\delta_{ik} \\ & - \tilde{\sigma}_{ik} - \sigma'_{ik} + \pi_{ik} \end{aligned} \tag{15}$$

and the notation has been introduced

$$p = -E_0 + TS + \mu\rho + \mathbf{w} \cdot \mathbf{j}_0 + \tilde{\sigma}_{ij}\tilde{u}_{ij} \tag{16}$$

In the derivatiopn of Eq.(14) we have neglected the term $\tilde{\sigma}_{ij}\tilde{u}_{ik}\partial v_{Lk}/\partial x_j$ that is small in framework of the linear elasticity theory. In addition, for the terms of the second order of infinitesimal in strains the approximation has been used

$$(\mathbf{v}_p - \mathbf{v}_L) \cdot \nabla(\tilde{\sigma}_{ik}\tilde{u}_{ik}) \simeq \mathbf{v}_p \cdot \nabla(\tilde{\sigma}_{ik}\tilde{u}_{ik})\,,$$

because the interstitial velocity is appreciably more than the lattice one.

The Eq.(15) defines the momentum current density of the medium. The comparison of the Eq.(14) with the energy conservation law (10) leads to the definition of: the energy current $\mathbf{Q}$

$$\begin{aligned} \mathbf{Q} = & \Big\{ (\frac{v_L^2}{2} + \mu + \frac{TS}{\rho})\,\mathbf{j} + \rho_p \mathbf{v}_p (\mathbf{v}_p \cdot \mathbf{w}) \\ & + \mathbf{q} - \mathbf{v}_L \cdot (\tilde{\sigma} + \sigma') + \mathbf{v}_p \cdot \pi \Big\}\,; \end{aligned} \tag{17}$$

the dissipative function R

$$\begin{aligned} R = {} & \sigma'_{ik}\frac{\partial v_{Li}}{\partial x_k} - \pi_{ik}\frac{\partial v_{pi}}{\partial x_k} - \frac{\mathbf{q}\nabla T}{T} \\ & - T\mathbf{J}\nabla\Big(\frac{\nu}{\rho T}\Big)\,; \end{aligned} \tag{18}$$

and the force $\mathbf{f}$

$$\mathbf{f} = \nabla p_{\scriptscriptstyle L} - \rho_{\scriptscriptstyle L}(\nabla\mu + \frac{S\nabla T}{\rho}) + \rho_{\scriptscriptstyle L}\frac{\nu}{\rho}\nabla c \\ - \tilde{u}_{ik}\nabla\tilde{\sigma}_{ik} \,. \tag{19}$$

In the framework of the linear theory the positive definiteness of R leads to the linear relationships relating the dissipative currents to the thermodynamic forces. Taking into account Onsager's reciprocity relations for the transport coefficients and time-reversal property of dissipative effects[1], we can write this relationships, at given σ'_{ik}, in the form

$$\begin{aligned} \pi_{ik} &= -\eta_{ikjm}\frac{\partial v_{pj}}{\partial x_m}\,, \\ q_i &= -\frac{\kappa_{ik}}{T}\frac{\partial T}{\partial x_k} - \alpha_{ik}T\frac{\partial}{\partial x_k}\Big(\frac{\nu}{\rho T}\Big)\,, \\ J_i &= -\frac{\alpha_{ik}}{T}\frac{\partial T}{\partial x_k} - \beta_{ik}T\frac{\partial}{\partial x_k}\Big(\frac{\nu}{\rho T}\Big)\,, \end{aligned} \tag{20}$$

where the fourth-rank tensor η is related to the impurity viscosity, the second-rank tensor κ has meaning of the pure heat conductivity, β is the second-rank tensor related to the interstitial diffusion and α is related to the cross effect of thermal diffusion of interstitials.

It is seen from the Eq.(15) that p, given by the Eq.(16), can be interpreted as "pressure" in the medium. The relation similar to the Gibbs-Duhem relation for fluid system follows from Eq.(16).

$$\rho d\mu = dp + \nu d\,c - SdT - \mathbf{j}_0 d\mathbf{w} - \tilde{u}_{ij}d\tilde{\sigma}_{ij}\,. \tag{21}$$

From (21) one obtains for gradients

$$\rho\nabla\mu + S\nabla T = \nabla p + \nu\nabla c - j_{0i}\nabla w_i - \tilde{u}_{ij}\nabla\tilde{\sigma}_{ij}\,.$$

Introducing this into the Eq.(19), we obtain the expression for the mass force as

$$\mathbf{f} = \nabla p_{\scriptscriptstyle L} - (1-c)\nabla p + c\rho_{\scriptscriptstyle L}\nabla\frac{w^2}{2} - c\tilde{u}_{ij}\nabla\tilde{\sigma}_{ij}\,. \tag{22}$$

This expression shows explicitly that in the limit $c \to 0$ the mass force vanishes provided that $p \to p_{\scriptscriptstyle L}$. From this condition it follows that it must be

$$p_{\scriptscriptstyle L} = -E_0 + TS + \mu\rho_{\scriptscriptstyle L} + \tilde{\sigma}_{ij}\tilde{u}_{ij}, \qquad (c=0).$$

The last relationship should be considered as the definition of the "pressure" $p_{\scriptscriptstyle L}$. Let us note that the similar expression has been used in Ref.[2] for a crystal with vacancies. In the same limit Π_{ik} coincides with the normal expression for a momentum current density $\Pi_{ik} = \rho_{\scriptscriptstyle L} v_{Li}v_{Lk} - \sigma_{ik} - \sigma'_{ik}$ and in the linear approximation in strains the expression (17) is reduced to the standard definition of the energy current density in the viscoelastic medium

$$\mathbf{Q} = (\frac{\rho v_{\scriptscriptstyle L}^2}{2} + E_0)\mathbf{v}_{\scriptscriptstyle L} - \mathbf{v}_{\scriptscriptstyle L}\cdot(\sigma + \sigma') + \mathbf{q}\,.$$

Having substituted the found expression for Π_{ik} and $\mathbf{f}$ in (3) and (6) and restricting to the linear terms in lattice strains, we obtain the complete set of the hydrodynamic equations for a crystal with interstitials

$$\begin{aligned} &\frac{\partial\rho}{\partial t} + \operatorname{div}\mathbf{j} = 0\,, \\ &\rho\frac{\partial c}{\partial t} + (\mathbf{j}\cdot\nabla)\,c + \operatorname{div}\mathbf{J} = 0\,, \\ &\frac{\partial S}{\partial t} + \operatorname{div}\Big(\frac{S}{\rho}\mathbf{j} + \frac{\mathbf{q}}{T} - \frac{\nu}{\rho T}\mathbf{J}\Big) = \frac{R}{T}\,, \\ &\rho_{\scriptscriptstyle L}\frac{\partial\mathbf{v}_{\scriptscriptstyle L}}{\partial t} + \rho_{\scriptscriptstyle L}(\mathbf{v}_{\scriptscriptstyle L}\cdot\nabla)\mathbf{v}_{\scriptscriptstyle L} = -(1-c)\nabla p \\ &\qquad\qquad + \nabla\cdot\tilde{\sigma} + \nabla\cdot\sigma' + c\rho_{\scriptscriptstyle L}\nabla\frac{w^2}{2}, \\ &\frac{\partial\mathbf{j}}{\partial t} + \mathbf{v}_{\scriptscriptstyle L}\operatorname{div}\mathbf{j} + (\mathbf{j}\cdot\nabla)\mathbf{v}_{\scriptscriptstyle L} + \mathbf{j}_0\operatorname{div}\mathbf{v}_p \\ &\qquad +(\mathbf{v}_p\cdot\nabla)\mathbf{j}_0 = -\nabla p + \nabla\cdot\tilde{\sigma} + \nabla\cdot\sigma' \\ &\qquad\qquad\qquad -\nabla\cdot\pi\,, \end{aligned} \tag{23}$$

where R and the dissipative currents are defined by expressions (18) and (20).In addition, the system (23) has to be still supplemented by the conservation energy law (10).

Now as a simplest example of the application of the obtained equations we shall consider the propagation of a sound in the infinite cristal with the low interstitial concentration. We shall assume that effects of the viscosity and the heat conductivity are absent so that the only dissipative process is related to the interstitial diffusion. In addition, we shall use the isotropic approximation for both the elastic stress tensor and the diffusion current, taking

$$\tilde{\sigma}_{ij} = 2\mu_0\tilde{u}_{ij}\,, \qquad \mathbf{J} = -T\beta\nabla\Big(\frac{\nu}{\rho T}\Big)\,,$$

where μ_0 is the shear modulus and the constant β is proportianal to the diffusion coefficient. Further we shall confine ourselves to the case of the small diffusion mobility of interstitials when $\beta \ll 1$. Assuming that a plane wave propagates along the x-direction and having eliminated the current $\mathbf{j}$, one writes the set of the linearized equations (23) in the form

$$\begin{aligned} &\ddot{\rho}' = \frac{\partial^2 p'}{\partial x^2} - \frac{4}{3}\mu_0\frac{\partial^3 u_x}{\partial x^3}\,, \\ &\rho\dot{c}' = T\beta\frac{\partial^2\overline{\nu}'}{\partial x^2}\,, \qquad (\overline{\nu} = \nu/\rho T)\,, \\ &\rho\dot{s}' = -\frac{\nu}{\rho}\frac{\partial^2\overline{\nu}'}{\partial x^2}\,, \qquad (s = S/\rho)\,, \\ &\rho_{\scriptscriptstyle L}\ddot{u}_x = -(1-c)\frac{\partial p'}{\partial x} + \frac{4}{3}\mu_0\frac{\partial^2 u_x}{\partial x^2}\,, \\ &\ddot{u}_y = c_t^2\frac{\partial^2 u_y}{\partial x^2}\,, \qquad \ddot{u}_z = c_t^2\frac{\partial^2 u_z}{\partial x^2}\,. \end{aligned} \tag{24}$$

Here the prime denotes small deviations of a variable from its equilibrium value which is without prime and

$s = S/\rho$ is the entropy per unit mass. It follows from the last two equations that in the assumed approximation the sound velocity of the transverse waves $c_t^2 = \mu_0/\rho_L$ does not depend on the interstitial concentration and coincides with its usual value in the isotropic elastic medium.

The equality (21) shows that p, c, T, w^2 and $\tilde{\sigma}_{ij}$ can be taken as the independent variables. Taking into account the fact that the scalar function can depend on the tensor $\tilde{\sigma}_{ij}$ by convolution $\tilde{\sigma}_{ij}\tilde{\sigma}_{ij}$ only, in the linear approxomation, one can consider ρ, $\overline{\nu}$, s to be functions of p, c, and T. In the following we shall take the space and time dependence of all variables to be of the form $exp[i\omega(t+x/v)]$, where v is the longitudinal sound velocity , and write down the set (24) as

$$\begin{aligned} & v^3\frac{\partial\rho}{\partial T}T' + \big(v^3\frac{\partial\rho}{\partial p} - v\big)p' + v^3\frac{\partial\rho}{\partial c}c' \\ & \qquad\qquad + \frac{4}{3}\mu_0 i\omega u_x = 0\,, \\ & i\omega T\beta(\frac{\partial\overline{\nu}}{\partial T}T' + \frac{\partial\overline{\nu}}{\partial p}p') + (i\omega T\beta\frac{\partial\overline{\nu}}{\partial c} - v^2\rho)c' \\ & \qquad\qquad\qquad = 0\,, \\ & \frac{\partial s}{\partial T}T' + \frac{\partial s}{\partial p}p' + (\frac{\partial s}{\partial c} + \overline{\nu})c' = 0\,, \\ & (1-c)vp' + i\omega(\rho_L v^2 - \frac{4}{3}\mu_0)u_x = 0\,. \end{aligned} \tag{25}$$

We shall find the sound velocity in the form $v = v_0 + \beta v_1$, where $\beta \to 0$. Having put in (25) $\beta = 0$ one finds zero approximation v_0 as

$$v_0^2 = \frac{4}{3}\frac{\mu_0}{\rho_L} + \Big(\frac{\partial s}{\partial T}\Big)_p \Big/ \frac{\partial(\rho,s)}{\partial(p,T)} + O(c)\,, \tag{26}$$

where $O(c)$ denotes the small terms to be proportianal a concentration c. Using the well known properties of a functional determinants, one has

$$\frac{\partial(\rho,s)}{\partial(p,T)} = \frac{\partial(\rho,s)}{\partial(p,s)}\frac{\partial(p,s)}{\partial(p,T)} = \Big(\frac{\partial\rho}{\partial p}\Big)_s\Big(\frac{\partial s}{\partial T}\Big)_p. \tag{27}$$

Since the adiabatic compression modulus per unit mass K_{ad} is defined as

$$\frac{1}{K_{ad}} = \frac{1}{\rho}\Big(\frac{\partial\rho}{\partial p}\Big)_s\,,$$

we have, instead of (27)

$$\frac{\partial(\rho,s)}{\partial(p,T)} = \frac{\rho}{K_{ad}}\Big(\frac{\partial s}{\partial T}\Big)_p.$$

Substitution of the last equality in the Eq.(26) yields

$$v_0^2 = \frac{4}{3}\frac{\mu_0}{\rho_L} + \frac{K_{ad}}{\rho_L}\,, \tag{28}$$

since $\rho \to \rho_L$ at $c \to 0$. The expression (28) coincides with usual value of the longitudinal sound velocity in the isotropic elastic medium.

The compatibility condition of the set of Eqs.(25) up to terms of the second order in β yields an equation for v_1. To avoid too combersome expressions we use a number of simplifying assumptions. It is known that when introducing an impure particle into a perfect crystal its volume changes in a macroscopic value. Therefore one can suppose that at $c \to 0$ $\partial\rho/\partial c$ has to be considerably more than all the other thermodynamic derivatives included into the set (25). In addition, we shall confine ourselves to the temperature region in which one can ignore a heat expansion and neglect by terms containing $\partial\rho/\partial T$. Then keeping in an expression for v_1 only terms to be proportianal to $\partial\rho/\partial c$, we obtain

$$v_1 = i\omega\frac{T\delta}{2\rho_L v_0}\Big(\frac{\partial\rho}{\partial c}\Big)_{pT}\,,$$

where

$$\begin{aligned} \delta = {} & \frac{\partial(\overline{\nu},s)}{\partial(p,T)}\Big(\frac{\partial s}{\partial T}\Big)^{-1}_{cp} \\ & \times\frac{2K_{ad}}{(2\rho_L v_0^2 + 3K_{ad})(\partial\rho/\partial p)_{cT} - 3\rho_L}. \end{aligned}$$

Allowing for $v = v_0 + \beta v_1$, one has for the absorption coefficient

$$\gamma_l = \frac{\omega^2 T\beta\delta}{2\rho_L v_0^3}\Big(\frac{\partial\rho}{\partial c}\Big)_{pT} \tag{29}$$

As it seen from Eq.(29) γ_l to be proportianal to ω^2 and the diffusion coefficient.

In conclusion, we have obtained the complete system of the hydrodynamic equations for a crystal with interstitials. These equations allow to describe the joint dynamics of the lattice and the impurity system and take into account the dissipative efects of the viscosity, the heat conductivity and the diffusion of interstitials. On the basis of found equations we have considered the problem of the propagation of plane waves in the crystal with small interstitial concentration and calculated the sound velocities and absorption coefficient provided that the viscosity and the heat conductivity are absent and the diffusion mobility of interstitials is small.

---

[*] E-mail: buchb@univer.omsk.su

[1] P.C. Martin, O. Parodi and P.S. Pershan, Phys. Rev. A**6**, 2401 (1972).

[2] P.D. Fleming and C. Cohen, Phys. Rev. B**13**, 500 (1976).

[3] B.M. Aizenbud and N.D. Gershon, Physica A**108**, 583 (1981).

[4] T.C. Lubensky, S. Ramaswamy and J. Toner, Phys. Rev. B**32**, 7444 (1985).

[5] A.M. Anile and S. Pennisi, Phys. Rev. B**46**, 13186 (1992).

[6] Z.W. Gortel and L.A. Turski, Phys. Rev. B**45**, 9389 (1992).

[7] A.M. Anile and O. Muscato, Phys. Rev. B**51**, 16728 (1995).

[8] H.T.C. Stoof, K. Mullen, M. Wallin and S.M. Girvin, Phys. Rev. B**53**, 5670 (1996).

[9] M.W. Wu, H.L. Cui, and N.J.M. Horing, Phys. Rev. B**54**, 2351 (1996).

[10] E.B. Sonin and W.F. Vinen, J. Phys.:Condens. Matter, **10**, 2191 (1998).

[11] I. Tokatly and O. Pankratov, Phys. Rev. B**60**, 15550 (1999).

[12] L.D. Landau and E.M. Lifshitz, *Mechanics of Fluids*, 2nd. ed. Course of Theoretical Physics Vol.6 (Pergamon Press, New York, 1987).

[13] I.M. Khalatnikov, *Theory of Superfluids* (Nauka, Moscow, 1971).

[14] A.F. Andreev and L.M. Lifshitz, Sov. Phys. JETP **29**, 1107 (1969).